



ELSEVIER

Contents lists available at ScienceDirect

## Materials Letters

journal homepage: [www.elsevier.com/locate/matlet](http://www.elsevier.com/locate/matlet)

# Synthesis of three-dimensional nanoporous graphene for use as surface-enhanced Raman scattering substrate



Zhiqiang Tu<sup>a</sup>, Shangfei Wu<sup>b</sup>, Fan Yang<sup>a</sup>, Yongfeng Li<sup>a,\*</sup>, Liqiang Zhang<sup>a</sup>, Hongwen Liu<sup>b,\*</sup>, Hong Ding<sup>b,c</sup>, Pierre Richard<sup>b,c</sup>

<sup>a</sup> State Key Laboratory of Heavy oil Processing, China University of Petroleum, Beijing 102249, China

<sup>b</sup> Institute of Physics, Chinese Academy of Sciences, Beijing 100190, China

<sup>c</sup> Collaborative Innovation Center of Quantum Matter, Beijing, China

## ARTICLE INFO

## Article history:

Received 16 January 2015

Accepted 27 March 2015

Available online 4 April 2015

## Keywords:

Chemical vapour deposition

Porous material

Raman

## ABSTRACT

We synthesized 3D nanoporous graphene by a chemical vapour deposition method with nanoporous copper as a catalytic substrate, and we show that the resulting nanoporous graphene has the same average pore size and the same morphology as the underlying copper substrate. Our surface-enhanced Raman scattering (SERS) investigation indicates that the nanoporosity of graphene significantly improves the SERS efficiency of graphene as a substrate, which is better than that of planar single-layer graphene substrates.

© 2015 Elsevier B.V. All rights reserved.

## 1. Introduction

Surface-enhanced Raman scattering (SERS), which consists in the enhancement of inelastic light scattering of molecules adsorbed on a surface, is an attractive analytical method able to provide quantitative structural information for analytes. Although this effect is most often generated by the strong local electromagnetic confinement resulting from rough metallic surfaces or nanostructures such as colloidal silver or gold nanoparticles [1,2], large SERS effect has been observed recently in dealloyed nanoporous metallic films [3,4]. Interestingly, three-dimensional (3D) architectures of graphene have also been synthesized recently [5], including continuous 3D-foam-like graphene with pore sizes of several hundred micrometres obtained by the metal-catalysed chemical vapour deposition (CVD) method using Ni substrates [6,7]. This is an encouraging development since graphene has many advantages over metal substrates, such as lower cost and better biocompatibility. In principle though, graphene as substrate does not support the electromagnetic mechanism (EM) for SERS because the surface plasmons on graphene are in the terahertz range rather than in the visible range [8]. However, SERS can also arise from a charge transfer between the adsorbed molecules and a substrate with proper chemical affinity with these molecules, and SERS has been reported for two-dimensional single-layer graphene [9–11]. Unfortunately, whether properly controlled nanoporosity can improve the SERS properties of graphene is

unknown. Here we present a study of SERS enhancement for nanoporous graphene (NG) with a 3D network of nanometre pore sizes. Our results indicate a significant SERS enhancement as compared to planar graphene and nanoporous copper (NC).

## 2. Experimental

The 3D NG used in this study has been synthesized by a CVD method with NC as catalytic substrate. In order to synthesize 3D NG, NC substrates with different pore size distributions are fabricated by dealloying 0.14 mm-thick Cu<sub>30</sub>Mn<sub>70</sub> alloys synthesized by a melt spinning method [12–14]. The pore size of NC is adjusted by changing the dealloying time of the erosion aqueous solution consisting of (NH<sub>4</sub>)<sub>2</sub>SO<sub>4</sub>·H<sub>2</sub>O (1 M L<sup>-1</sup>) and MnSO<sub>4</sub>·H<sub>2</sub>O (0.01 M L<sup>-1</sup>). Then, NC substrates are used to synthesize NG films by a CVD process using a mixture of gases with a composition of CH<sub>4</sub>: Ar: H<sub>2</sub>=8: 200: 20 sccm min<sup>-1</sup>. Owing to the high activity of NC, the growth temperature is lowered to 600–900 °C. Finally, to investigate the SERS effect from 3D NG itself without the influence of the NC substrate, the 3D NG is released by etching graphene/NC stacks in aqueous FeCl<sub>3</sub> solution, then rinsed in deionized water and finally transferred to a Si substrate.

## 3. Results and discussion

Fig. 1 shows the scanning electron microscopy (SEM) images of NCs with average pore sizes ranging from 23 to 40 nm, which can also be observed in a cross sectional SEM image of NC (Fig. S1).

\* Corresponding authors.

E-mail addresses: [yfli@cup.edu.cn](mailto:yfli@cup.edu.cn) (Y. Li), [hliu@iphy.ac.cn](mailto:hliu@iphy.ac.cn) (H. Liu).




Fig. 1. SEM images of nanoporous coppers with different pore sizes: (a) 23 nm, (b) 28 nm, (c) 33 nm and (d) 40 nm.

Fig. 2a shows the cross-sectional SEM image of NG obtained after etching NC. The porous morphology of NG is shown in Fig. 2b. Our transmission electron microscopy (TEM) characterization of NG indicates that it consists of continuous 3D porous graphene (Fig. 2c), which is only one layer at the edge, as shown in Fig. S2. The selected area electron diffraction image displayed in Fig. 2d exhibits hexagonal spots in one circle, implying that the NG sample has a single crystal structure. From these experiments we conclude that the NG films grown on the NC surfaces have similar nanoporous structure as the underlying NC templates.

We further study the NG films using a Horiba JY-T64000 Raman spectrometer. In Fig. 3a we show the Raman spectra of NG films synthesized at different temperatures via NC substrates with 33 nm pore size. All G peaks, associated with the degree of graphitization, are found around  $1590\text{ cm}^{-1}$ . Strong and broad D and 2D modes are observed, which can be understood in terms of high disorder induced from edges and nanoclusters [15–17]. A downshift of the D peak from  $1364$  to  $1347\text{ cm}^{-1}$  is observed with the synthesis temperature increasing. Samples obtained at  $600$  and  $700\text{ }^{\circ}\text{C}$  show poor crystal structure (Fig. S3), whereas  $800\text{ }^{\circ}\text{C}$  is suitable to obtain NG with good quality, as displayed in Fig. 2c and d. Raman spectra of NG samples synthesized on NC substrates with different pore sizes at the optimized synthesis temperature of  $800\text{ }^{\circ}\text{C}$  are shown in Fig. 3b. Because of some melting of NC substrates (as shown in Fig. S4) with different pore sizes, NG samples eventually show very similar structures (as shown in Fig. 2a and b) without obvious differences in the Raman spectra.

We now discuss the SERS properties of NG using rhodamine 6G (R6G) as a probed molecule. First, the NG films have been transferred from the NC substrates onto  $\text{SiO}_2/\text{Si}$  substrates. Then, R6G molecules are deposited on a NG substrate by soaking them in

R6G solutions for 30 min. After soaking, the samples are dried naturally. The setup for Raman detection of R6G on a plain 3D NG substrate is schematically drawn in Fig. 4a.

We show in Fig. 4b the Raman spectra of  $10^{-5}\text{ M}$  R6G obtained on NG, NC, multi-layer graphene (MLG, 10 layers, CVD method) and single-layer graphene (SLG, CVD method) substrates. The fabrication method of MLG and SLG is discussed in detail in our previous work [18]. According to our findings, the SERS enhancement follows the sequence:  $\text{NG} > \text{SLG} \gg \text{NC} \gg \text{MLG}$ . This phenomenon is attributed to the strong interaction between NG and R6G through the photo-induced charge transfer and  $\pi$ - $\pi$  interactions. Fig. 4b clearly indicates that the SERS intensity of NG is higher than that of SLG substrates. It has been reported that the excitation of intrinsic graphene plasmons are tuneable and strengthened by natural nanoscale inhomogeneities, such as wrinkles [19,20]. Most likely, the better SERS efficiency of NG than SLG suggests that enhancement of the local electromagnetic field due to porosity and surface roughness plays an important role in tuning the plasmonic properties of these materials [21].

#### 4. Conclusions

3D-foam-like graphene films with nanopore sizes have been synthesized by a CVD method with NC as substrates, and the resulting nanoporous graphene has a similar porous structure as the underlying NC substrates. The Raman enhancement effect has been investigated by using R6G molecules. Our results indicate that NG has a great potential as SERS substrate that is better than those of NC, MLG and even SLG.




Fig. 2. SEM images of NG with (a) a side view and (b) a top view, (c) a typical TEM image, and (d) a SAED image of NG synthesized on a 33 nm NC under 800 °C.




Fig. 3. (a) Raman spectra of 3D NG samples synthesized at different temperatures on 33 nm NC substrates. (b) Raman spectra of NG samples on different NC substrates prepared at 800 °C. The laser power is 30 mw.




Fig. 4. (a) Scheme of Raman detection of R6G on a plain 3D NG substrate. Raman signals of R6G on different substrates (b). The laser power is 30 mw. The fluorescence background of R6G in (b) has been removed from the spectra.

## Acknowledgements

This work was supported by the National Natural Science Foundation of China (Nos. 21322609, 51071175 and 11274362), the Ministry of Science and Technology of China (No. 2011CBA001000), the Science Foundation Research Funds Provided to New Recruitments of China University of Petroleum, Beijing (2462014QZDX01) and Thousand Talents Program.

## Appendix A. Supporting information

Supplementary data associated with this article can be found in the online version at <http://dx.doi.org/10.1016/j.matlet.2015.03.131>.

## References

- [1] Lee PC, Meisel D. Adsorption and surface-enhanced Raman of dyes on silver and gold sols. *J Phys Chem* 1982;86:3391–5.
- [2] Freeman RG, Grabar KC, Allison KJ, Bright RM, Davis JA, Guthrie AP, et al. Self-assembled metal colloid monolayers: an approach to SERS substrates. *Science* 1995;267:1629–32.
- [3] Chen LY, Yu JS, Fujita T, Chen MW. Nanoporous copper with tunable nanoporosity for SERS applications. *Adv Funct Mater* 2009;19:1221–6.
- [4] Liu H, Zhang L, Lang X, Yamaguchi Y, Iwasaki H, Inouye Y, et al. Single molecule detection from a large-scale SERS-active Au<sub>79</sub>Ag<sub>21</sub> substrate. *Sci Rep* 2011;1:112.
- [5] Nardecchia S, Carriazo D, Ferrer ML, Gutierrez MC, del Monte F. Three dimensional macroporous architectures and aerogels built of carbon nanotubes and/or graphene: synthesis and applications. *Chem Soc Rev* 2013;42:794–830.
- [6] Chen ZP, Ren WC, Gao LB, Liu BL, Pei SF, Cheng HM. Three-dimensional flexible and conductive interconnected graphene networks grown by chemical vapour deposition. *Nat Mater* 2011;10:424–8.
- [7] Li N, Chen Z, Ren W, Li F, Cheng HM. Flexible graphene-based lithium ion batteries with ultrafast charge and discharge rates. *Proc Natl Acad Sci USA* 2012;109:17360–5.
- [8] Rana F. Graphene terahertz plasmon oscillators. *IEEE Trans Nanotech* 2008;7:91–9.
- [9] Ling X, Xie L, Fang Y, Xu H, Zhang H, Kong J, et al. Can graphene be used as a substrate for Raman enhancement? *Nano Lett* 2010;10:553–61.
- [10] Ling X, Moura LG, Pimenta MA, Zhang J. Charge-transfer mechanism in graphene-enhanced Raman scattering. *J Phys Chem C* 2012;116:25112–8.
- [11] Ling X, Wu J, Xie L, Zhang J. Graphene-thickness-dependent graphene-enhanced Raman scattering. *J Phys Chem C* 2013;117:2369–76.
- [12] Weissmüller J, Newman RC, Jin HJ, Hodge AM, Kysar JW. Nanoporous metals by alloy corrosion: formation and mechanical properties. *MRS Bull* 2009;34:577–86.
- [13] Hayes JR, Hodge AM, Biener J, Hamza AV, Sieradzki K. Monolithic nanoporous copper by dealloying Mn–Cu. *J Mater Res* 2006;21:2611–6.
- [14] Erlebacher J, Aziz MJ, Karma A, Dimitrov N, Sieradzki K. Evolution of nanoporosity in dealloying. *Nature* 2001;410:450–3.
- [15] Ferrari AC, Meyer JC, Scardaci V, Casiraghi C, Lazzeri M, Mauri F, et al. Raman spectrum of graphene and graphene layers. *Phys Rev Lett* 2006;97:187401.
- [16] Ryu S, Maultzsch J, Han MY, Kim P, Brus LE. Raman spectroscopy of lithographically patterned graphene nanoribbons. *ACS Nano* 2011;5:4123–30.
- [17] Ferrari AC, Robertson J. Interpretation of Raman spectra of disordered and amorphous carbon. *Phys Rev B* 2000;61:14095–107.
- [18] Tu ZQ, Liu ZC, Li YF, Yang F, Zhang LQ, Zhao Z, et al. Controllable growth of 1–7 layers of graphene by chemical vapour deposition. *Carbon* 2014;73:252–8.
- [19] Grigorenko AN, Polini M, Novoselov KS. Graphene plasmonics. *Nat Photon* 2012;6:749–58.
- [20] Crassee I, Orlita M, Potemski M, Walter AL, Ostler M, Seyller T, et al. Intrinsic terahertz plasmons and magnetoplasmons in large scale monolayer graphene. *Nano Lett* 2012;12:2470–4.
- [21] Maier SA. *Plasmonics: Fundamentals and Applications*. New York: Springer; 2007.

## Supporting Information

### Synthesis of three-dimensional nanoporous graphene and its surface-enhanced Raman scattering as a substrate

Zhiqiang Tu <sup>a</sup>, Shangfei Wu <sup>b</sup>, Fan Yang <sup>a</sup>, Yongfeng Li <sup>a,\*</sup>, Liqiang Zhang <sup>a</sup>, Hongwen Liu <sup>b,\*</sup>, Hong Ding <sup>b,c</sup>, Pierre Richard <sup>b,c</sup>

<sup>a</sup> State Key Laboratory of Heavy oil Processing, China University of Petroleum, Beijing, 102249, China

<sup>b</sup> Institute of Physics, Chinese Academy of Sciences, Beijing, 100190, China

<sup>c</sup> Collaborative Innovation Center of Quantum Matter, Beijing, China

E-mail addresses: [yfli@cup.edu.cn](mailto:yfli@cup.edu.cn) (Y. Li); [hliu@iphy.ac.cn](mailto:hliu@iphy.ac.cn) (H. Liu)




Fig. S1 A cross-sectional SEM picture of 33 nm NC






Fig. S2 High resolution TEM images of NG. The arrows show that single layer graphene exists in the samples.




Fig. S3 TEM and SAED images of NG obtained at 600 and 700 °C.




Fig. S4 A SEM of 33 nm NC with graphene grown on its surface